


ACTMIX NDBC-75GE F200

Antioxidant NDBC (NBC)

A C T I V E M A T E R I A L		PROPERTIES:	Rubber antioxidant NDBC mainly used for SBR, CR, CSPE (chlorosulfonated polyethylene) and other synthetic rubbers to prevent checking sunlight and ozone and promote heat resistance of CR and CSPE. It is a light stabilizer and anti-ozone agent for polymers in plastic industry. It is a stabilizer for polypropylene fibers, thin films and narrow-band but leads to a yellowish-green appearance of the product.	TYPICAL VALUES:	Melting point: 86°C Purity: Min 96% Ni content: 12.0-13.0% Heating loss content: Max 0.50%
		M		Nickel	
	A	dibutyldithiocarbamate			
	T	C ₁₈ H ₃₆ N ₂ S ₄ Ni			
	E	M.W.: 467.45			
	R	CAS: 13927-77-0			
I	EINECS: 237-696-2	DOSAGE:	0.3-0.5phr usually.		

M A S T E R B A T C H	PRODUCT	Active Content (%)	Appearance	Filtration (µm)	Binder	Sulfur Content (%)	Density (g/cm ³)	
	Actmix NDBC-75GE F200	75	Dark-green Granules	200	EPDM/EVM	20.0	1.00	
	E	* Binder type can be customized. Except EPDM/EVM, ECO also can be available for.						
	R	SAFETY&TOXICITY:						
	B	Please refer to related SDS.						
	A	PACKAGING&STORAGE:						
T	Net weight 25kg/PE bags lined carton; Net weight 600 kg/pallet.							
C	Shelf-life : 1 year in its original packaging							
H	Stored in a dry and cool place.							

Compared to traditional NDBC powders, Actmix NDBC-75GE F200 allows:

Dust free products with a complete filtration up to 100µm, production environment improver.

Effective guarantee of activity of NDBC due to pre-dispersed masterbatch.

Tack free products at room temperature, convenience and accuracy on ingredients.

Lower Mooney viscosity at lower temperature (50°C), higher quality of dispersion.

Impurity free, blocked filter free of extrusive products, scrap rate reduction and higher productivity thanks to filtration.

Wider compatibility with other elastomers.

G: granule, P: plate, E: EPDM binder, N: NBR binder, S: SBR binder, A: ACM binder, EO: ECO binder, F200: filtration and micron number of filter

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.